

Certificate of Assessment

Job No.: NK8011

No. 2510

"Copyright CSIRO 2018 ©"
Copying or alteration of this report
without written authorisation from CSIRO is forbidden.

This is to certify that the specimen described below was tested by the CSIRO Infrastructure Technologies in accordance with Australian/ New Zealand Standard 3837, Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter, 1998, at 50 kW/m², on behalf of:

Borg Manufacturing Pty Limited
2 Wella Way
SOMERSBY NSW 2250
AUSTRALIA

A full description of the test specimen and the complete test results are detailed in the Division's sponsored investigation report numbered FNK 12181.

SAMPLE

IDENTIFICATION: Chromaboard

DESCRIPTION OF

SAMPLE: The sponsor described the tested specimen as a dyed medium density fibreboard (MDF) comprised of wood fibres, wax and resin.

Nominal total thickness: 8 mm to 25 mm
Nominal density: 750 kg/m³
Colours: black

SAMPLE

CLASSIFICATION: Group Number: Group 3
(In accordance with A2.4 of the Building Code of Australia.)^{1,2}
Average specific extinction area: 1.2 m²/kg
(Refer to Specification C1.10 section 4 of the Building Code of Australia.)^{1,2}

Notes:

1. The results of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.
2. As per Section 9 (n) of AS 5637.1:2015, the determination of the group number was based on the AS/NZS 3837:1998 test, and was deemed valid in the cone calorimeter for the assignment of National Construction Code (NCC) group number.

Testing Officer: Faustin Molina Date of Test: 12 June 2018

Issued on the 3rd day of July 2018 without alterations or additions.



Brett Roddy
Team Leader, Fire Testing and Assessments



NATA Accredited Laboratory
Number: 165
Corporate Site No 3625
Accredited for compliance with ISO/IEC 17025 - Testing.

CSIRO INFRASTRUCTURE TECHNOLOGIES

14 Julius Avenue, Riverside Corporate Park, North Ryde NSW 2113 AUSTRALIA
Telephone: 61 2 9490 5444 Facsimile: 61 2 9490 5555 www.csiro.au



Certificate of Test

Quote No.: NE8010

REPORT No.: FNE12182

AS/NZS 1530.3:1999 SIMULTANEOUS DETERMINATION OF IGNITABILITY, FLAME PROPAGATION, HEAT RELEASE AND SMOKE RELEASE

TRADE NAME: Chromaboard

SPONSOR: Borg Manufacturing Pty Limited
2 Wella Way
SOMERSBY NSW 2250
AUSTRALIA

DESCRIPTION OF

SAMPLE: The sponsor described the tested specimen as a dyed medium density fibreboard (MDF) comprised of wood fibres, wax and resin binder.

Nominal total thickness: 8 mm to 25 mm
Nominal density: 750 kg/m³
Colour: black

TEST PROCEDURE: Nine samples were tested in accordance with AS/NZS 1530, Method for fire tests on building components and structures, Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release, 1999. For the test, each sample was clamped to the specimen holder in four places.

RESULTS: The following means and standard errors were obtained:

Parameter	Mean	Standard Error
Ignition Time (min)	5.7	0.1
Flame Spread Time (s)	N/A	N/A
Heat Release Integral (kJ/m ²)	26.0	2.2
Smoke Release (log ₁₀ D)	-1.406	0.035

For regulatory purposes these figures correspond to the following indices:

Ignitability Index (0-20)	Spread of Flame Index (0-10)	Heat Evolved Index (0-10)	Smoke Developed Index (0-10)
14	0	1	3

The results of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

DATE OF TEST: 15 June 2018

Issued on the 3rd day of July 2018 without alterations or additions.



Faustin Molina
Testing Officer



Brett Roddy
Team Leader, Fire Testing and Assessments

Copyright CSIRO 2018 ©. Copying or alteration of this report without written authorisation from CSIRO is forbidden.



NATA Accredited Laboratory
Number: 165
Corporate Site No 3625

Accredited for compliance with ISO/IEC 17025 – Testing.

CSIRO INFRASTRUCTURE TECHNOLOGIES

14 Julius Avenue, Riverside Corporate Park, North Ryde NSW 2113 AUSTRALIA
Telephone: 61 2 9490 5444 Facsimile: 61 2 9490 5555 www.csiro.au

