

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

Test Sponsor : Borg Manufacturing Pty Ltd
2 Wella Way
Somersby NSW 2250

Test Number : 19-003250
Issue Date : 16/08/2019
Print Date : 16/08/2019

Sponsor Product Clients Ref : "Custompine Raw 16mm"
Sample of Particleboard
Colour : Natural
End Use : Joinery and Shelving
Nominal Composition : Radiata Pine
Nominal Mass per Unit Area/Density : 650kg/m3
Nominal Thickness : 16mm

Product Group Number Classification : 3
Average Specific Extinction Area : 23.3 m²/kg



Fiona McDonald
Testing Technologist

36805

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited . Please contact us by collect call so that arrangements can be made at our expense to rectify the error.