

# polytec imi-beton high pressure laminate

## General Information

polytec's imi-beton Laminate Flex is suited for all vertical applications and curved surfaces. Available in four raw finished colours, while the pre-finished and pre-sealed sister product, imi-beton Laminate Plus, is a pioneering and durable polished concrete surface solution.

## Features & Benefits

- Industrial aesthetics - Beautiful and elegant modern industrial look
- Machinability - Low abrasive material which facilitates ease of machining and fabrication
- Flexibility - imi-beton Flex can easily be shaped around curved surfaces

## Product Properties

PROPERTY	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT	LAMINATE GRADE
Thickness	EN 438-2.5	thickness	mm	$0,6 \leq S \leq 1,0 \pm 0,15$
Length and Width	EN 438-2.6	length and width	mm	+ 10 / - 0
Straightness of edges	EN 438-2.7	maximum deviation	mm / m	$\leq 1,5$
Squareness	EN 438-2.8	maximum deviation	mm / m	$\leq 1,5$
Flatness	EN 438-2.9	maximum deviation*	mm / m	$\leq 100$
Resistance to immersion in boiling water	EN 438-2.12	appearance	rating (min) Polished finish Raw finish	$\geq 3$ $\geq 4$
Resistance to dry heat (180°C)	EN 438-2.16	appearance	rating (min) Polished finish Raw finish	$\geq 3$ $\geq 4$
Stability at elevated temperature	EN 438-2.17	cumulative dimensional change	% long % transv.	$\leq 0,55$ $\geq 1,05$
Resistance to cracking (thin laminates)	EN 438-2.23	appearance	rating (min)	$\geq 4$
Volume electrical resistance	EN 61340-4-1	Rv (23°C / 50% RH)	Ohm	$1 \times 10^9 - 1 \times 10^{11}$
Density	ISO 1183	density	gr/cm <sup>3</sup>	$\geq 1,35$

## Contact

For further information on this product contact:

polytec (ABN 11 123 216 124), 2 Wella Way, Somersby, NSW 2250, Australia

Telephone: 1300 300 547 Fax: 1300 320 547

---

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.

---

Date of last update: 30 March 2016