

Technical Data

Light Reflectance Value (LRV)

Light Reflectance Value (LRV)

Light reflectance value (LRV), is a measure of visible and usable light that is reflected from a surface when illuminated by a light source. The table below shows the average LRV values measured for a range of **polytec** colours.

The colour tone of wood grain prints and stone structures can differ significantly depending on the position of the surface area measured. Generally it is difficult to get a consistent LRV value for wood grain or stone patterns and the value shown is an average unlike solid colours which reflect a consistent result.

LRVs published in **polytec** marketing and technical materials are provided as a guide to assist specification. Minor variations may occur due to manufacturing processes, colour variation and testing conditions. Where projects require specific LRV compliance, it is recommended that values be confirmed using.

Colour	LRV
Adriatic	8.6
Agave	30.8
Alabaster	83
Alboran Stone	66
Aluminium	40.4
Amaro	63.7
Angora Oak	46.2
Anthracite Metallic	4.1
Antico Oak	25.8
Antique	78.5
Arabica	9.2
Arcadia Oak	18.7
Arctic Ice	85.4
Ardesia Stone	7.2
Argento Stone	69.5
Artisan Oak	17.9
Aspen Stone	71.6
Aston White	71.4
Athena Stone	8.3
Australian Native	18
Avion Grey	57.3
Barrington Marble	10.2
Beige Travertine	55.2
Belgian Oak	8.9



Scan the QR code for the latest **Light Reflectance Value** document.

Colour	LRV
Bernini Marble	32.3
Bespoke	41.4
Black	6
Black Ply	7.9
Black Wenge	6.5
Blanco Marquina	73.5
Bleached Walnut	65.7
Blossom White	81.4
Bone White	83.1
Boston Oak	33.6
Botanic	7.8
Bottega Oak	8.6
Bottocino	53.2
Bronze Gold Leaf	27.4
Buller Stone	77.6
Café Cream	66.2
Calacutta D'oro	71.2
Calacutta Grey	65.1
Canterbury Grey	17.9
Carrara	70.9
Casentino Beech	39.5
Castel	32.7
Catalina Marble	7.6
Cavia Lini	10.3
Chambord	74.9
Champagne Metallic	40
Char Oak	13.4
Charcoal Fabrini	10.6
Cinder	10.1
Classic White	86.7
Cloudy Grey	48.6
Coastal Oak	42
Combat Teak	14.4
Concrete Fabrini	29.7
Copper Leaf	27.2
Corsica	55.2
Cosmic Granite	12.6
Cream	90

Colour	LRV
Crema Lini	50.7
Crisp White	86.1
Dark Cement	12.2
Dawnshade	63.56
Desideria Marble	16.4
Drifted Oak	50.3
Elemental Grey	38.6
Emperor Stone	23.7
Empire Oak	10.4
Estella Oak	8.6
European Walnut	14.3
Evergreen	12.8
Feldspar Shimmer	8.3
Ferro	11.5
Florentine Walnut	15.8
Fontaine	44.2
Forage	14.6
French Stone	60.1
Gesso Lini	45.6
Gossamer White	71.4
Graphite	10.7
Greige	53.5
Grey Cement	38
Grey Taj	45
Greystone	24.9
Grigio Marble	17.8
Habitat	12.6
Havana Oak	13.3
Husk	70.9
Italian Cotton	39.8
Ivorio Travertine	63.1
Jamaican Walnut	8
Jasmine	82.5
Lava	7.8
Light Brass Leaf	50.6
Lightstone	78.82
Ligurian Walnut	49
Maison Oak	32.4

Colour	LRV
Malt	52.9
Marina Grey	38.3
Marmo di Monte	64.6
Marmo di Torre	70.7
Marni Lini	51.8
Maroso Milan	19.4
Mercurio Grey	12.7
Mineral Metallic	12.2
Mink	15.9
Montage	54
Moss Grey	59.7
Natural Cotton	62.3
Natural Oak	39.2
Natural Ply	58.5
Natural White	87.4
Navona Stone	37.4
Navy	6.6
Nero Granite	12
New Antique White	83.9
New Ultra White	89.9
Nickel	33.1
Nomad	32.84
Nordic Oak	54.6
Norfolk Terrazzo	57.5
Notaio Walnut	17.8
Nouveau Grey	37.6
Oasis	20.1
Obsidian Metallic	5.4
Ochre Figured-Wood	19.9
Onyx Figured-Wood	7.4
Oxford	6
Oyster Grey	56
Palace Teak	36.5
Palatino	52.1
Pallido	51.3
Palomera Oak	31.6
Papyrus	75.2
Parchment	83.9

Colour	LRV
Pearl Fabrini	65.2
Pearl Metallic	80.4
Perugian Walnut	8.2
Pewter Metallic	27.2
Phantom Black	3
Pietra Stone	46
Plantation Ash	43.8
Platinum Leaf	27.6
Polar White	88.1
Porcelain	74.5
Portland Stone	39.2
Portofino Stone	57.4
Prime Oak	28.4
Provincial Limestone	46.9
Pure Gold Leaf	31.4
Quartiera Maple	60.7
Rocco Lini	25.8
Rojo Walnut	11.7
Roman Ceppo	34.3
Rose Gold Leaf	32
Royal Oyster	66.8
Rubra Oak	12.1
Serene	31.4
Shannon Oak	8.3
Sienna Figured-Wood	14.1
Silk	62.9
Snow Fabrini	74.9
Soft Walnut	51.8
Solara	49.09
Sterling	23.2
Stone Fabrini	36.8
Stone Grey	36.5
Storm	8
Strata Grey	25.1
Superior White	83.6
Taj Mahal	57
Tasmanian Oak	30.4
Taupe	31

Colour	LRV
Temple Stone	49.5
Tessuto Milan	28.6
Titanium	15.3
Tivoli Ceppo	62.9
Topiary	22.7
Truffle Lini	10.2
Tunisia Stone	16.4
Tuross Oak	41.3
Ultra White	92
Urban Slate	37.1
Verdelho	52
Vesuvius Ceppo	19
Visoni Stone	28.4
Volcanic Stone	9.4
White	86.4
White Cement	63.4
White Cotton	82.9
White Mist	72.4
Whitewood	68.8
Wild Clay	42.76
Wisewood	49.05



Scan the QR code for the latest
Light Reflectance Value document.

Contact

For further information contact:

Porta Products Pty. Ltd. (ABN 31 003 246 357)

Address 2 Wella Way,
Somersby NSW 2250,
Australia

Telephone 1300 300 547

Fax 1300 320 547

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.